

KYDEX® 150

Class I/A rated thermoplastic sheet

Introduction

KYDEX® 150 is a proprietary thermoplastic alloy sheet that is used for laminating and thermoforming applications requiring a Class I/A building code.

General Information

The Class I/A building code is rated up to and including 1.52mm (0.060") and Class II/B building codes up to and including 2.36mm (0.093") and is Underwriters Laboratories, Inc® listed.

Suggested Applications

- Protective Wall Covering Systems
- Miscellaneous Applications

Features

- Good formability and extensibility
- Easy to work with once formed
- Available in standard thicknesses from 0.71mm (0.028") to 2.36mm (0.093"), various textures, over 3,500 colours, custom blank sizes.
- Stronger cleaning agents can be used with no discoloration or damage to surface material
- More resistant to a wider range of concentrated chemicals
- Not available for field applied wallcovering applications. Please contact SEKISUI SPI Customer Service with your requirements.

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Material Safety Data Sheets, please call 800.325.3133.

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997

techservice@sekisui-spi.com

sekisui-spi.com

KYDEX® 150

Class I/A rated thermoplastic sheet

Physical Properties

Property	Test Method	Typical Value ¹	
Specific Gravity	ASTM D-792	1.35	
Tensile Strength	ASTM D-638	42 MPa	6,100 psi
Flexural Strength	ASTM D-790	64 MPa	9,300 psi
Modulus of Elasticity	ASTM D-790	2,310 MPa	335,000 psi
Notched Izod Impact Resistance, @ 23°C (73°F)	ASTM D-256	961 J/m	18 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	94	
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	78.3°C	173°F
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) unannealed	ASTM D-648	68.8°C	156°F
Flammability: ² Flame Spread/Smoke Developed 1.27mm (0.050") or less	UL-723	25 40	
Flammability: ² Flame Spread/Smoke Developed 1.52mm (0.060") or less	UL-723	20 350	
Flammability: ² Flame Spread/Smoke Developed 2.38mm (0.93") or less	UL-723	35 350 - 450	

¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified.
² Underwriters Laboratories, Inc®, File R6738 (N)
 Not intended for specification purposes.

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Outside the US: +1.570.389.5814
 Fax: 800.452.0155, +1.570.387.7786
 Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
 Fax: +1.570.387.8722
 Outside the US: +1.570.387.6997
 techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.